



Sole UK Distributors Of
REINHARDT-TECHNIK
Metering, Mixing &
Dispensing Systems



Bonham Drive, Eurolink Industrial Estate
Sittingbourne, Kent. ME10 3RY
Tel 01795 427888 Fax 01795 479685
Email: sales@eurobond-adhesives.co.uk
Web: www.eurobond-adhesives.co.uk

Technical Data Sheet

PENLOC ZT

Penloc ZT is a low-strength anaerobic adhesive.

TECHNICAL DATA

Colour	Yellow
Resin	Acrylate
Strength	Low Strength
Max gap fill	0.1mm

UNCURED PROPERTIES

Viscosity (Brookfield LVT)	200 mPas
Flash point	> 100°C
Density	approx 1.12g/cm ²

Curing

Handling strength	5 – 20 min
Functional strength	45 – 300 min
Full strength	6 – 24 hrs

CURED PROPERTIES

Temperature resistance	-55 to 150°C
Breakaway Torque	12.5 Nm
Prevailing Torque	12 Nm
Pressure resistance	11.5 N/mm ²
Dielectric strength	8.5 kV/mm

10.01.2000

No liability is accepted for any injury, loss or damage arising directly from the use of the Company's products or from the use of information given in our publications, which is intended to serve as a guide only. Customers should satisfy themselves by appropriate trials that the products are suitable for their intended use.

